



TECHNICAL SHEET



Product name:

DENATOP PZ/AU

Page: 1/2

Date: 13.4.2016

Characteristics:	Single-layer anticorrosion paint for industrial applications
Description:	Single-pack water-thinnable anticorrosion single-layer paint formulated on the basis of special acrylic and alkyd resins.
Composition (general):	Mixture based on acrylic and alkyd resins containing anticorrosion and color-fast pigments, fine extenders, coalescent agents and other ingredients enhancing its properties. As a thinner, it contains water and a small amount of glycol-ether-based solvents; it does not contain any aromatic solvents or white spirit.
Application:	Anticorrosion surface treatments of metal structures, products and semi-finished products in mechanical engineering and other branches of the metal industry. The product is suitable mainly for applications at stable temperatures in paint shops and for application with the heat curing of products. The application should always be discussed with the manufacturer.
Colors:	It is made according to RAL, EUROTREND, NCS, ČSN color charts or in the agreed color shades.
Properties:	Paint:
Density (g/cm³):	1.1 - 1.3
Volume solids ONL (%):	35 - 45
Weight solids (%):	35 - 55
KU viscosity:	70 - 120
Flow time by use of flow cups F6 (s):	20 - 280
pH (at 20 °C):	8 - 10
VOC (volatile organic compounds) (kg/kg):	0.005 - 0.09
0.006 TOC (total organic carbon content) (kg/kg):	0.003 - 0.05
Maximum permissible value of VOC content (g/l):	140
Max. VOC content in the product in the ready-to-use condition (g/l):	120
Water-thinnable paint category:	A/i single-pack paints with a special function.
Appearance/color:	liquid
Gloss value (at 60°):	70 - 90
Pendulum hardness (2H/80 °C):	min. 30%
Miscibility:	Miscible with water.
Adhesion by the grid-cutting method:	Degree 0 (cut edges are completely smooth and free of any defects)
Drying, degree 1 (surface dry):	1 hr
Drying time, degree 2 (dry to the touch):	2 hrs
Drying time, degree 4 (dry-through):	4 hrs
Substrate preparation:	The substrate must be dry, free from any mechanical and greasy impurities, and residues of old paint incoherent with the substrate. Recommended substrate treatments include sand blasting, blasting, degreasing or phosphatizing.
Application conditions:	It is recommended that the application method and the application conditions are always discussed with the manufacturer, who will adapt the composition of the paint to the specific conditions. The air and substrate temperatures during the coat application and drying must not fall below +15 °C, a min. of 3 °C above the dew point, a max. humidity of 70 vol. %. If multiple coatings are required, the time lag between individual coatings should be at least 12 hrs, depending on the drying conditions.
Thinning:	Water
Recommended method of application:	With a paint brush, a paint roller or by soaking or spray painting - air, pneumatic, high-pressure - Airless, Airmix
Recommended coating system:	1 layer of DENAPUR PZ/AU, optimum paint thickness of 60 - 120 µm DFT, the re-spray interval with two layers is 12 hrs at 20 °C; if additional drying is employed at temperatures to 80 °C, the interval can be reduced up to 2 hrs.



TECHNICAL SHEET



Product name:

DENATOP PZ/AU

Page: 2/2

Date: 13.4.2016

Application data:	The paint can be additionally dried at a max. of 80 °C.												
Spreading capacity and recommended thickness:	The recommended coat thickness ranges from 60 to 120 µm DFT, which depends mainly on the substrate roughness												
	<table border="1"><tr><td>Wet-film thickness WFT (µm)</td><td>130</td><td>270</td></tr><tr><td>Dry-film thickness DFT (µm)</td><td>60</td><td>120</td></tr><tr><td>Theoretical spreading rate (m²/kg)</td><td>5.80</td><td>2.90</td></tr><tr><td>Theoretical spreading rate (kg/m²)</td><td>0.20</td><td>0.35</td></tr></table>	Wet-film thickness WFT (µm)	130	270	Dry-film thickness DFT (µm)	60	120	Theoretical spreading rate (m ² /kg)	5.80	2.90	Theoretical spreading rate (kg/m ²)	0.20	0.35
	Wet-film thickness WFT (µm)	130	270										
	Dry-film thickness DFT (µm)	60	120										
	Theoretical spreading rate (m ² /kg)	5.80	2.90										
Theoretical spreading rate (kg/m ²)	0.20	0.35											
Packaging:	Plastic or metal containers weighing 0,8 - 200 kg.												
Storage:	Store in original and well-closed containers in cool, dry and well-ventilated areas at temperature from +5 to +25 °C. Protect from freezing. Keep the mixture separated from drinks, foodstuff, feedstuff and medicine. Store away from the reach of children. The shelf life is a minimum of 12 months from the date of manufacture. The product must not freeze.												
Disposal of packaging and waste:	Product residues and contaminated packaging shall be disposed of as hazardous waste in accordance with the applicable regulations.												
Safety and hygiene:	When handling the product, observe the instructions provided in the safety data sheet. Observe the principles of personal hygiene. If on the skin, wash the affected areas with soap and water. If in the eyes: rinse with water. If swallowed, rinse mouth with water, do not induce vomiting. In case of health difficulties, seek medical attention.												
Legislation, certificates, attestations, other tested parameters:	See the Declaration of Conformity												